



Exterior Below-Grade Residential Waterproofing Membrane

# Mar-flex TopGun Waterbase Emulsion Waterproofing

## Description

The Mar-flex TopGun Waterbase (WB) Elastomeric Emulsion Exterior Below-Grade Waterproofing Membranes are tested and proven membranes that can be applied over almost any clean, dry, sound substrate. It features our highest Residential "Limited-Lifetime" warranty and is a waterproofing industry product leader.

## Uses

TopGun WB is recommended for new construction waterproofing of all below-grade basement walls of poured concrete, unit masonry construction or ICF walls. TopGun WB can be used as a membrane spray only or as part of a system.

## Leeds Data

Mar-flex TopGun WB membrane is considered a GREEN product and can be used toward LEEDS building credits.

## Equipment

For maximum product output, Mar-flex recommends the use of airless spray equipment. A pressure of 3000 psi is required to spray the membrane.

## Coverage

Depending on porosity and roughness of surface, coverage rate for spray application should be 4-5 gallons per 100 ft<sup>2</sup>. Final application should be a minimum of a 60-mil wet thickness resulting in 40-mil dry.

## General Requirements

Avoid application when inclement weather is present or imminent. Do not apply the TopGun WB membrane when the air temperature is below 20° F. Ensure that footings are exposed, and all surfaces are free of any debris, loose material, form oils, wet/damp or frozen areas. Sweep the tops of footers to clear away debris and dry footings/walls. May be applied to "Green" concrete as soon as forms are removed. Make sure that all existing pipe, conduit or any other penetration through the wall are properly sealed on the outside with water plug, hydraulic cement or similar product. If penetrations are to be added after the spray application, it is still the applicators responsibility to ensure these areas are sealed. If this responsibility is passed onto the builder, inform the builder they are responsible and inform them of the proper procedure to seal these areas.

## Required Prep Work

Remove below grade wall ties inside the basement and out. Patch all outside below grade ties holes with the Mar-flex 362 Mastic or similar. Poured concrete walls must be free of voids and honeycombs. Any such areas, if present, should be

covered with the Mar-flex 362 Mastic or similar. All brick ledges must be properly capped and sealed.

## Application Information

When spraying TopGun WB, the final recommended spray temperature of the material should be 100°F - 140°F. Recommended tip sizes: Graco XHD631,635,731, or 735.

CAUTION: Prolonged heat can deteriorate water-based products inside the spray tank. NOTE: When transporting water-based material from site to site or when idle on a jobsite, the heat exchanger must remain off and there should be no other type of heat source to the tanks. **To flush equipment: Diesel Fuel. Total clean up: Xylene. Thinning not recommended.**

## Spray Installation

Membrane application should be done a section of the wall at a time. Use multiple, uniform passes, alternating from horizontal to vertical. Application should end on wall at footer. As work progresses check for thin spots and voids in the spray application. Re-spray any areas as necessary to obtain the required mil thickness. Determine the wet mil thickness by using a standard wet mil gauge. Application should be made to all below-grade basement walls. This includes any wall that would be considered a common wall to habitable/storage areas. (Ex. garage wall, porch, etc.) Note: Please see the individual instruction sheet for the proper way to install the board or roll that you are using.

## Backfilling/Drainage

Backfilling should begin no sooner than 24 hours after the installation of the Mar-flex TopGun WB Exterior Below-Grade Waterproofing System but must be backfilled within 15 days. #57 Gravel or equivalent must be no less than 6" to 2' high at the base of the foundation and 1' in depth away from the foundation walls. Adequate interior and exterior foundation drainage at the base of the foundation walls or across any floors must be properly installed and working. Gutters and downspouts must be installed and functioning properly. Adequate drainage in landscaping beds adjacent to the foundation must be installed. Final grade must not extend above the waterproofing system and must slope away from the foundation at a minimum of 1/2" per foot for the first 12' from the structure.

## Shipping Water-Based Product

When shipping emulsion-based products during the winter months, there is always a risk of the material freezing while in transport. Please plan accordingly as product is freeze/thaw sensitive.



*Exterior Below-Grade Residential Waterproofing Membrane*

# Mar-flex TopGun Waterbase Emulsion Waterproofing

## Storage of Water-Based Product

The TopGun WB, like all asphalt emulsions, must be kept from freezing. It is best to store product containers off the floor at an ambient temperature at 40°F and above. Opened drums should be tightly sealed before storage to prevent a skim-coat from developing on the surface of the liquid.

## Packaging

TopGun WB Waterproofing Membrane is available in 55-Gallon Drums, 330-Gallon Totes and Bulk (6,000 Gallons).

## Shelf Life

When stored at temperatures between 40°- 100° shelf life is 6 months in the original, unopened container.

## Limited Lifetime Warranty

Mar-flex Waterproofing & Building Products warrants this product to be free of defects in workmanship and materials only at the time of shipment from our factory. If any Mar-flex materials prove to contain manufacturing defects that substantially affect their performance, Mar-flex will, at its option, replace the materials or refund its purchase price. This limited lifetime warranty is the only warranty extended by Mar-flex with respect to its materials. There are no other warranties, including the implied warranties or merchantability & fitness for a particular purpose. Mar-flex specifically disclaims liability for any incidental, consequential, or other damages, including but not limited to, loss of profits or damages to a structure or its contents, arising under any theory of law whatsoever. The dollar value of Mar-flex's liability and buyer's remedy under this limited warranty shall not exceed the purchase price of the Mar-flex material in question. Fully transferable to subsequent homeowner. See Mar-flex for complete details.

**HEALTH AND SAFETY INFORMATION IS GIVEN IN THE SAFETY DATA SHEET AND THE PRODUCT DATA SHEET AVAILABLE FOR THIS PRODUCT. THESE SHOULD BE READ AND UNDERSTOOD BEFORE USING THIS PRODUCT.**

Mar-flex TopGun Water Base Spec Sheet		
Property	Method	Results
Color		Black
Total Solids		78%
Application Method		Spray
Application Range		20° to 130° F
Elongation @ 73.4° F	(ASTM D-412 Method A)	4485% min
Crack Bridging Ability	(ASTM C-836)	10 cycles; no failure
Wind driven Rain Resistance to Hydrostatic Head Pressure	(Federal Spec TT-C-555B, Par 4.4.7) ASTM D5385	No Water Infiltration Passed @6psi/13.9ft of head pressure
Total Cure Time		24 hrs.
Weight/Gallon		7.5 lbs,
Coverage Rate		20-25-sqft/gal
Tensile Strength	(ASTM-C-719)	48 psi min.
Water Vapor Permeance/Transmission	(ASTM E-96)	0.35 perms (g/h-sq.ft.-in.Hg) 0.11(grains/sq.ft./h)
Mold Growth/Bacterial Attack		No Degradation
Membrane		60 mil wet thickness
Adhesion to Concrete		No Adhesion Loss

sm1.20